## Technical specifications Marmoleum meets the requirements of EN-ISO 24011

Marmoleum

Marmoleum Acoustic meets the requirements of EN 687 Marmoleum Decibel meets the requirements of EN 686











			Marmoleum Real/Fresco/Vivace/ Splash/Terra 2.5 mm	Marmoleum Real/Fresco 3.2mm	Marmoleum Decibel	Marmoleum Acoustic
×	Total thickness	EN-ISO 24346	2.5 mm	3.2 mm	3.5 mm	4.0 mm
	Surface finish		Topshield <sup>2</sup>	Topshield <sup>2</sup>	Topshield <sup>2</sup>	Topshield <sup>2</sup>
ji.	Domestic use	EN-ISO 10874	Class 23	Class 23	Class 23	Class 23
	Commercial use	EN-ISO 10874	Class 32	Class 34	Class 33	Class 33
jih.	Light Industrial use	EN-ISO 10874	Class 43	Class 43	Class 41	Class 41
÷Ω	Roll width	EN-ISO 24341	2.00 m	2.00 m	1.90 / 2.00 m	2.00 m
$\blacksquare$	Collection size		90 colours	8 colours	14 colours All colours available as made to order.	6 colours
<b>-</b> §	Roll length	EN-ISO 24341	≤ 33 m	≤ 33 m	≤ 33 m	≤ 33 m
	Residual indentation Typical value	EN-ISO 24343-1	≤ 0.15 mm ~0.08 mm	≤ 0.15 mm ~0.10 mm	≤ 0.15 mm ~0.20 mm	≤ 0.15 mm ~0.25 mm
<b>a</b>	Castor chair continuous use	ISO 4918/ EN 425	Suitable for office chairs with castors			
₹.	Light fastness	EN-ISO 105-B02	Method: 3 blue scale minimum 6.			
9	Flexibility	EN-ISO 24344	ø 40 mm	ø 50 mm	ø 40 mm	ø 60 mm
<b>©</b>	Resistance to chemicals EN-ISO 26987 Resistant to diluted acids, oils, fats and to the conventional solvents. Not resistant to prolonged exposure to a					
Bacteriostatic properties* Marmoleum has natural bacteriostatic properties which are confirmed by independent laboratories, ever						, even against the bacteria M
Cigarette resistance EN 1399 There is no melting of the surface by cigarettes. Marks left on Marmoleum as a result					Narmoleum as a result of stubbed-	out cigarettes can be remove
/ <u>/</u>	Electrical resistance Marmoleum Ohmex	EN 1081	$1-10^6 < R1 < 1-10^8 \Omega$ static dissipative	-	-	-
ŝ	Acoustical impact sound reduction	EN-ISO 717-2	≤ 5 dB	≤ 6 dB	≤ 18 dB	≤ 14 dB
W	Indoor Air Emissions: TVOC at 28 days	EN 16516	< 0,05 mg/m <sup>3</sup>	< 0,05 mg/m <sup>3</sup>	< 0,05 mg/m <sup>3</sup>	< 0,05 mg/m <sup>3</sup>
LCA	Life Cycle Assessment**		LCA is the foundation for securing the lowest environmental impact.			
<b>@</b>	Creating better environments					
<b>₽</b>	CO <sub>2</sub> neutral		Marmoleum 2.0 mm and 2.5 mm are produced CO2 neutral.**			
	renewable electricity		Marmoleum is manufactured using 100% electricity from renewable sources.			
	natural materials (e.g. linseed oil, jute, tree resin, wood flour, limestone)		Marmoleum is made of 94-98% natural materials.			
			Marmoleum contains PEFC certified wood flour.			
			Marmoleum is free of PVC, PET, synthetic rubber and plasticizers.			
3	recycled content		Marmoleum contains recycled content.			
<b>=</b>	Application on underfloor heating		yes	yes	yes	yes
	Marmoleum meet the require	ments of EN 14041				
Ξ.	Product code	EN 14041	0100201-DoP-306	0100201-DoP-306	0100201-DoP-306	0100201-DoP-306
an)	Reaction to fire	ISO 9239-1	CRF 9.2 kW/m² Smoke Dvlp 78%.min	CRF 5.6 kW/m² Smoke Dvlp 330%.min	CRF 5.1 kW/m² Smoke Dvlp 338%.min	CRF 6.8 kW/m² Smoke Dvlp 380%.min
(\$\)		AS 4586:2013	R10	R10 P2*	R10 P2*	R10 P2*
	Slip resistance	A3 4360.2013	P2*	F Z		
92.)	Slip resistance Body voltage	EN 1815	P2* ≤ 2 kV	≤ 2 kV	≤ 2 kV	≤ 2 kV

 $<sup>{}^*\,\</sup>text{Marmoleum sheet can be installed nett fit, or with a welding rod in the seam. Both are proven hygienic solutions.}$ 

Marmoleum 2.5mm, 3.2mm and acoustic, Forbo recommends using 414 Euroflex lino plus and for Marmoleum decibel use 540 Eurosafe special.

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001.

All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001.

The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on all of our websites.



## DOWNLOADS:

Marmoleum | slip report | AS 4586 Marmoleum warranty pack

Marmoleum 2.5mm | fire report | AS 9239-1 Marmoleum cleaning & maintenance Marmoleum 2.5mm | fire report (walls) AS 3837 Marmoleum sheet installation guide

All other documents can be found be clicking on the following link: **Download centre** 



<sup>\*\*</sup> For verification and details please consult our Marmoleum EPD.

 $<sup>\</sup>star$  Slip test result achieved in an independent laboratory on new sample. On-site testing is variable and may not guarantee the same result. For sustainable slip a particle based floor must be used.